


## Data sheet, Maxell Zinc Air 10 PR536



### Specifications:

Chemical system: Zinc / Air  
Typical Capacity: 100 mAh\*  
IEC High Drain Test Capacity: 87 mAh\*\*\*  
Weight: approx 0,3 g  
Storage: 10-30 °C / 20-80 % r.h.  
Short Exposition: -10-65 °C / 5-95 % r.h.

Nominal voltage: 1,45 V  
IEC Standard Test Capacity: 90 mAh\*\*  
Impedance: max. 12 Ω@ 1kHz  
Volume: approx 0,085 ccm  
Operating: 0-45 °C / 25-70 % r.h.

\*1000 Ohms 12h/day to 0.9V at 20 °C / 55% r.h.

\*\*IEC Hearing aid standard test 1,05 V at 20 °C / 55% r.h. according to IEC 60086-2:2015/DIN EN 60086-2:2016

\*\*\*IEC High Drain Test to 1,1 V at 20 °C / 55% r.h. according to IEC 60086-2:2015/DIN EN 60086-2:2016

### Dimensions:

according to IEC 60086-2:2015/DIN EN 60086-2:2016

IEC: PR 70

### Typical discharge characteristics at 20 °C / 55% r.h.:

